

Aclo Accutech Polypropylene Homopolymer HP0339M30L Mica Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Mica Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0339M30L-Mica-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	MD; ASTM D955
Melt Flow	20 g/10 min	20 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	75	75	ASTM D785
Tensile Strength at Break	28.0 MPa	4060 psi	ASTM D638
Tensile Strength, Yield	31.0 MPa	4500 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	3.299 GPa	478.5 ksi	ASTM D638
Flexural Strength	45.0 MPa	6530 psi	ASTM D790
Flexural Modulus	3.699 GPa	536.5 ksi	ASTM D790
Izod Impact, Notched	0.342 J/cm	0.640 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 °C	250 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	78.9 °C	174 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China