

## Aclo Accutech Polypropylene Homopolymer HP0339T30L Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Homopolymer-HP0339T30L-Talc-Reinforced.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0339T30L-Talc-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	MD; ASTM D955
Melt Flow	21 g/10 min	21 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	84	84	ASTM D785
Tensile Strength at Break	28.0 MPa	4060 psi	ASTM D638
Tensile Strength, Yield	32.0 MPa	4640 psi	ASTM D638
Elongation at Break	14 %	14 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	2.299 GPa	333.5 ksi	ASTM D638
Flexural Strength	45.0 MPa	6530 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.251 J/cm	0.470 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 °C	257 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.2 °C	144 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China