

Aclo Accutech Polypropylene Homopolymer HP0339T30L1 Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0339T30L1-Talc-Reinforced.php

| Physical Properties | Metric | English | Comments |
|-----------------------|--------------|---------------------------|---------------|
| Density | 1.13 g/cc | 0.0408 lb/in ³ | ASTM D792 |
| Linear Mold Shrinkage | 0.0090 cm/cm | 0.0090 in/in | MD; ASTM D955 |
| Melt Flow | 21 g/10 min | 21 g/10 min | ASTM D1238 |
| Ash | 30 % | 30 % | ASTM D2584 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|------------|----------------|-----------|
| Hardness, Rockwell R | 83 | 83 | ASTM D785 |
| Tensile Strength at Break | 30.0 MPa | 4350 psi | ASTM D638 |
| Tensile Strength, Yield | 34.0 MPa | 4930 psi | ASTM D638 |
| Elongation at Break | 10 % | 10 % | ASTM D638 |
| Elongation at Yield | 4.0 % | 4.0 % | ASTM D638 |
| Tensile Modulus | 2.20 GPa | 319 ksi | ASTM D638 |
| Flexural Strength | 47.0 MPa | 6820 psi | ASTM D790 |
| Flexural Modulus | 3.20 GPa | 464 ksi | ASTM D790 |
| Izod Impact, Notched | 0.251 J/cm | 0.470 ft-lb/in | ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|---|---------|---------|-----------|
| Deflection Temperature at 0.46 MPa (66 psi) | 130 °C | 266 °F | ASTM D648 |
| Deflection Temperature at 1.8 MPa (264 psi) | 71.1 °C | 160 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China