

Aclo Accutech Polypropylene Homopolymer HP0339W30L Wollastonite Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0339W30L-Wollastonite-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	MD; ASTM D955
Melt Flow	21 g/10 min	21 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	86	86	ASTM D785
Tensile Strength at Break	28.0 MPa	4060 psi	ASTM D638
Tensile Strength, Yield	31.0 MPa	4500 psi	ASTM D638
Elongation at Break	12 %	12 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	3.00 GPa	435 ksi	ASTM D638
Flexural Strength	42.0 MPa	6090 psi	ASTM D790
Flexural Modulus	3.299 GPa	478.5 ksi	ASTM D790
Izod Impact, Notched	0.299 J/cm	0.560 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 °C	257 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	77.2 °C	171 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China