

Adamas Adalon® 206 PTFE, 15/5% Glass/MoS2 Filled

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Glass Filled, Molded

Material Notes:

Information provided by Adamas, HPM

Order this product through the following link:

http://www.lookpolymers.com/polymer_Adamas-Adalon-206-PTFE-155-GlassMoS2-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.26 - 2.28 g/cc	2.26 - 2.28 g/cc	ASTM D792
Deformation	5.4 - 7.1 %	5.4 - 7.1 %	Permanent deformation after 24 hrs @ 23°C; ASTM D621
	11 - 13 %	11 - 13 %	ASTM D621

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	56 - 60	56 - 60	ASTM D2240
Tensile Strength at Break	>= 19.0 MPa	>= 2760 psi	ASTM D4894
Elongation at Break	>= 200 %	>= 200 %	ASTM D4894
Coefficient of Friction, Dynamic	0.080 - 0.12	0.080 - 0.12	ASTM D1894
Coefficient of Friction, Static	0.10 - 0.15	0.10 - 0.15	ASTM D1894

Thermal Properties	Metric	English	Comments
Melting Point	327 °C	621 °F	DSC
Maximum Service Temperature, Air	260 °C	500 °F	DSC
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	DSC
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China