

## Addiplast Addilene J 370 Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

**Material Notes:**High impact strength, high elongation at break  
Information provided by Addiplast.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Addiplast-Addilene-J-370-Polypropylene-Copolymer.php](http://www.lookpolymers.com/polymer_Addiplast-Addilene-J-370-Polypropylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ISO 1183/A
Melt Flow	5.0 g/10 min	5.0 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	63	63	ISO 868
Tensile Strength at Break	18.0 MPa	2610 psi	ISO R 527
Tensile Strength, Yield	22.0 MPa	3190 psi	ISO R 527
Elongation at Yield	>= 500 %	>= 500 %	ISO R 527
Modulus of Elasticity	0.950 GPa	138 ksi	ISO 178
Izod Impact, Notched (ISO)	NB	NB	ISO 180/1A
Charpy Impact Unnotched	NB	NB	ISO 179/IeU
Charpy Impact, Notched	4.00 J/cm <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	ISO 179/IeA

Thermal Properties	Metric	English	Comments
Melting Point	165 - 168 °C	329 - 334 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	48.0 °C	118 °F	ISO 75-2/AF
Vicat Softening Point	141 °C	286 °F	ISO 306/A50

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	CEI 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	CEI 60093
Comparative Tracking Index	>= 600 V	>= 600 V	CEI 60112/Solution A

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**