

## Addiplast Addilene J 490 M40S Flame Retardant Polypropylene, 40% Mineral Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant , Polypropylene, Mineral Reinforced

### Material Notes:

Flame retardant, mineral filled, with halogens Information provided by Addiplast.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Addiplast-Addilene-J-490-M40S-Flame-Retardant-Polypropylene-40-Mineral-Filled.php](http://www.lookpolymers.com/polymer_Addiplast-Addilene-J-490-M40S-Flame-Retardant-Polypropylene-40-Mineral-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in <sup>3</sup>	ISO 1183/A
Melt Flow	12 g/10 min	12 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	72	72	Conditioned; ISO 868
Tensile Strength at Break	24.0 MPa	3480 psi	Conditioned; ISO R 527
Elongation at Break	7.0 %	7.0 %	Conditioned; ISO R 527
Modulus of Elasticity	3.80 GPa	551 ksi	Conditioned; ISO 178
Izod Impact, Notched (ISO)	2.50 kJ/m <sup>2</sup>	1.19 ft-lb/in <sup>2</sup>	Conditioned; ISO 180/1A
Charpy Impact Unnotched	2.00 J/cm <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	Conditioned; ISO 179/1eU
Charpy Impact, Notched	0.250 J/cm <sup>2</sup>	1.19 ft-lb/in <sup>2</sup>	Conditioned; ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	165 - 168 °C	329 - 334 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	69.0 °C	156 °F	ISO 75-2/AF
Vicat Softening Point	152 °C	306 °F	ISO 306/A50
Flammability, UL94	V-2 @Thickness 1.60 mm	V-2 @Thickness 0.0630 in	
Oxygen Index	23 %	23 %	ISO 4589
Glow Wire Test	960 °C	1760 °F	CEI 60695/2/1

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	Conditioned; CEI 60093

Electrical Properties	Metric	English	Comments
Dielectric Strength	42.0 kV/mm	1070 kV/in	CEI 60243-1
Comparative Tracking Index	>= 600 V	>= 600 V	CEI 60112/Solution A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China