

## Addiplast Addilene J 522 K20 Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

**Material Notes:**

High density Information provided by Addiplast.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Addiplast-Addilene-J-522-K20-Polypropylene-Copolymer.php](http://www.lookpolymers.com/polymer_Addiplast-Addilene-J-522-K20-Polypropylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in <sup>3</sup>	ISO 1183/A
Melt Flow	20 g/10 min	20 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	72	72	ISO 868
Tensile Strength at Break	10.0 MPa	1450 psi	ISO R 527
Modulus of Elasticity	3.10 GPa	450 ksi	ISO 178
Izod Impact, Notched (ISO)	4.00 kJ/m <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	ISO 180/1A
Charpy Impact Unnotched	5.50 J/cm <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy Impact, Notched	0.400 J/cm <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	165 - 168 °C	329 - 334 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75-2/AF
Vicat Softening Point	152 °C	306 °F	ISO 306/A50

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 600 V	>= 600 V	CEI 60112/Solution A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China