

Addiplast Addilene PMD 50245 Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

For electroplating Information provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addilene-PMD-50245-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183/A
Melt Flow	15 g/10 min	15 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	ISO 868
Tensile Strength at Break	26.0 MPa	3770 psi	ISO R 527
Tensile Strength, Yield	28.0 MPa	4060 psi	ISO R 527
Elongation at Yield	50 %	50 %	ISO R 527
Modulus of Elasticity	2.00 GPa	290 ksi	ISO 178
Izod Impact, Notched (ISO)	3.50 kJ/m ²	1.67 ft-lb/in ²	ISO 180/1A
Charpy Impact Unnotched	NB	NB	ISO 179/IeU
Charpy Impact, Notched	0.350 J/cm ²	1.67 ft-lb/in ²	ISO 179/IeA

Thermal Properties	Metric	English	Comments
Melting Point	165 - 168 °C	329 - 334 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75-2/AF
Vicat Softening Point	153 °C	307 °F	ISO 306/A50

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	CEI 60093
Surface Resistance	1.00e+11 ohm	1.00e+11 ohm	CEI 60093
Comparative Tracking Index	>= 600 V	>= 600 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China