

Addiplast Addilene PMD 50272 Flame Retardant Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant

Material Notes:

Flame retardant, high rigidity Information provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addilene-PMD-50272-Flame-Retardant-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ISO 1183/A
Melt Flow	16 g/10 min	16 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	79	79	Conditioned; ISO 868
Tensile Strength at Break	65.0 MPa	9430 psi	Conditioned; ISO R 527
Elongation at Break	4.0 %	4.0 %	Conditioned; ISO R 527
Modulus of Elasticity	5.50 GPa	798 ksi	Conditioned; ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	2.30 J/cm ²	10.9 ft-lb/in ²	Conditioned; ISO 179/leU
Charpy Impact, Notched	0.650 J/cm ²	3.09 ft-lb/in ²	Conditioned; ISO 179/leA

Thermal Properties	Metric	English	Comments
Melting Point	165 - 168 °C	329 - 334 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	141 °C	286 °F	ISO 75-2/AF
Vicat Softening Point	162 °C	324 °F	ISO 306/A50
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
Oxygen Index	23 %	23 %	ISO 4589
Glow Wire Test	850 °C	1560 °F	CEI 60695/2/1

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	Conditioned; CEI 60093

Surface Resistance Electrical Properties	$\geq 1.00e+13$ ohm Metric	$\geq 1.00e+13$ ohm English	Conditioned; CEI 60093 Comments
Comparative Tracking Index	≥ 600 V	≥ 600 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China