

Addiplast Addinyl A2 ZG30 Nylon 66, 30% Glass Bead

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Bead Filled

Material Notes:

Glass bead reinforced, improved stiffness and dimensional stability, increased thermal aging stability Information provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addinyl-A2-ZG30-Nylon-66-30-Glass-Bead.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	Conditioned; ISO 868
	87	87	ISO 868
Tensile Strength at Break	60.0 MPa	8700 psi	Conditioned; ISO R 527
	80.0 MPa	11600 psi	ISO R 527
Elongation at Yield	7.0 %	7.0 %	ISO R 527
	11 %	11 %	Conditioned; ISO R 527
Modulus of Elasticity	1.80 GPa	261 ksi	Conditioned; ISO 178
	3.80 GPa	551 ksi	ISO 178
Izod Impact, Notched (ISO)	3.50 kJ/m ²	1.67 ft-lb/in ²	ISO 180/1A
	7.00 kJ/m ²	3.33 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	ISO 179/leU
	6.00 J/cm ²	28.6 ft-lb/in ²	Conditioned; ISO 179/leU
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	ISO 179/leA
	0.500 J/cm ²	2.38 ft-lb/in ²	Conditioned; ISO 179/leA

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 μm/m-°C	33.3 μin/in-°F	ASTM E831
Melting Point	260 °C	500 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	ISO 75-2/AF

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Dielectric Strength	25.0 kV/mm	635 kV/in	Conditioned; CEI 60243-1
	30.0 kV/mm	762 kV/in	CEI 60243-1
Comparative Tracking Index	600 V	600 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China