

Addiplast Addinyl A2H M30 Flame Retardant Nylon 66, 30% Mineral Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Mineral Filled

Material Notes:

Flame retardant, 30% mineral filled, with halogens Information provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addinyl-A2H-M30-Flame-Retardant-Nylon-66-30-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.62 g/cc	0.0585 lb/in ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	81	81	Conditioned; ISO 868
	86	86	ISO 868
Tensile Strength at Break	50.0 MPa	7250 psi	Conditioned; ISO R 527
	72.0 MPa	10400 psi	ISO R 527
Elongation at Break	3.0 %	3.0 %	ISO R 527
	8.0 %	8.0 %	Conditioned; ISO R 527
Modulus of Elasticity	4.00 GPa	580 ksi	Conditioned; ISO 178
	7.50 GPa	1090 ksi	ISO 178
Izod Impact, Notched (ISO)	3.00 kJ/m ²	1.43 ft-lb/in ²	ISO 180/1A
	4.00 kJ/m ²	1.90 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	2.50 J/cm ²	11.9 ft-lb/in ²	ISO 179/leU
	4.00 J/cm ²	19.0 ft-lb/in ²	Conditioned; ISO 179/leU
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	ISO 179/leA
	0.400 J/cm ²	1.90 ft-lb/in ²	Conditioned; ISO 179/leA

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	ISO 75-2/AF
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Thermal Properties	Metric	English	Comments
Glow Wire Test	960 °C	1760 °F	CEI 60695/2/1

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	CEI 60093
Comparative Tracking Index	300 V	300 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China