

## Addiplast Addinyl B2 ZV30 Nylon 6, 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

### Material Notes:

Glass fiber reinforced, increased thermal aging stability Information provided by Addiplast.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Addiplast-Addinyl-B2-ZV30-Nylon-6-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Addiplast-Addinyl-B2-ZV30-Nylon-6-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	76	76	Conditioned; ISO 868
	83	83	ISO 868
Tensile Strength at Break	110 MPa	16000 psi	Conditioned; ISO R 527
	170 MPa	24700 psi	ISO R 527
Elongation at Yield	3.0 %	3.0 %	ISO R 527
	5.0 %	5.0 %	Conditioned; ISO R 527
Modulus of Elasticity	4.80 GPa	696 ksi	Conditioned; ISO 178
	8.20 GPa	1190 ksi	ISO 178
Izod Impact, Notched (ISO)	14.0 kJ/m <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	ISO 180/1A
	22.0 kJ/m <sup>2</sup>	10.5 ft-lb/in <sup>2</sup>	Conditioned; ISO 180/1A
Charpy Impact Unnotched	6.50 J/cm <sup>2</sup>	30.9 ft-lb/in <sup>2</sup>	ISO 179/leU
	7.50 J/cm <sup>2</sup>	35.7 ft-lb/in <sup>2</sup>	Conditioned; ISO 179/leU
Charpy Impact, Notched	1.10 J/cm <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	ISO 179/leA
	1.90 J/cm <sup>2</sup>	9.04 ft-lb/in <sup>2</sup>	Conditioned; ISO 179/leA

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 μm/m-°C	16.7 μin/in-°F	ASTM E831
Melting Point	220 °C	428 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ISO 75-2/AF

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Dielectric Strength	30.0 kV/mm	762 kV/in	Conditioned; CEI 60243-1
	35.0 kV/mm	889 kV/in	CEI 60243-1
Comparative Tracking Index	550 V	550 V	CEI 60112/Solution A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China