

Addiplast Addinyl C2 V30 Nylon 66/6, 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6, 30% Glass Fiber Reinforced

Material Notes:

Glass fiber reinforced, high strength Information provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addinyl-C2-V30-Nylon-666-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	78	78	Conditioned; ISO 868
	84	84	ISO 868
Tensile Strength at Break	115 MPa	16700 psi	Conditioned; ISO R 527
	175 MPa	25400 psi	ISO R 527
Elongation at Yield	4.0 %	4.0 %	ISO R 527
	6.0 %	6.0 %	Conditioned; ISO R 527
Modulus of Elasticity	4.70 GPa	682 ksi	Conditioned; ISO 178
	8.10 GPa	1170 ksi	ISO 178
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	ISO 180/1A
	21.0 kJ/m ²	9.99 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179/leU
	7.50 J/cm ²	35.7 ft-lb/in ²	Conditioned; ISO 179/leU
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/leA
	1.80 J/cm ²	8.57 ft-lb/in ²	Conditioned; ISO 179/leA

Thermal Properties	Metric	English	Comments
CTE, linear	35.0 μm/m-°C	19.4 μin/in-°F	ASTM E831
Melting Point	243 °C	469 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	230 °C	446 °F	ISO 75-2/AF

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Dielectric Strength	30.0 kV/mm	762 kV/in	Conditioned; CEI 60243-1
	35.0 kV/mm	889 kV/in	CEI 60243-1
Comparative Tracking Index	550 V	550 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China