

## Adell BH-18 Nylon 6, 40% Mineral Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 40% Mineral Filled

**Material Notes:**

Data provided by Adell Plastics, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Adell-BH-18-Nylon-6-40-Mineral-Filled.php](http://www.lookpolymers.com/polymer_Adell-BH-18-Nylon-6-40-Mineral-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.90 %	0.90 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	95	95	ASTM D785
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Ultimate	86.2 MPa	12500 psi	ASTM D638
Elongation at Break	12.5 %	12.5 %	ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	5.20 GPa	754 ksi	ASTM D790
Compressive Yield Strength	186 MPa	27000 psi	ASTM D695
Izod Impact, Notched	0.500 J/cm	0.937 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	222 °C	432 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	182 °C	360 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	289 °F	ASTM D648
Flammability, UL94	HB	HB	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China