

Adell BT-13 Nylon 6, 15% Glass Reinforced; Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass Filled , Impact Grade

Material Notes:

Data provided by Adell Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Adell-BT-13-Nylon-6-15-Glass-Reinforced-Impact-Modified.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ASTM D792
Water Absorption	1.0 %	1.0 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.0075 cm/cm	0.0075 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	78	78	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	93.1 MPa	13500 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	4.10 GPa	595 ksi	ASTM D790
Compressive Yield Strength	97.0 MPa	14100 psi	ASTM D695
Izod Impact, Notched	1.20 J/cm	2.25 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	216 °C	421 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	199 °C	390 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	188 °C	370 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China