

Adell ER-16 Homopolymer Polypropylene, 30% Glass Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Data provided by Adell Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Adell-ER-16-Homopolymer-Polypropylene-30-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.0035 cm/cm	0.0035 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	60	60	ASTM D785
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Ultimate	89.6 MPa	13000 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Strength	138 MPa	20000 psi	ASTM D790
Flexural Modulus	5.90 GPa	856 ksi	ASTM D790
Izod Impact, Notched	1.00 J/cm	1.87 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.30 J/cm	8.06 ft-lb/in	ASTM D256
Gardner Impact	0.300 J	0.221 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Melting Point	182 °C	360 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	154 °C	309 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China