

## Adell EZ-16 Homopolymer Polypropylene, 30% Calcium Carbonate Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Calcium Carbonate (CaCO3) Filler

**Material Notes:**

Data provided by Adell Plastics, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Adell-EZ-16-Homopolymer-Polypropylene-30-Calcium-Carbonate-Filled.php](http://www.lookpolymers.com/polymer_Adell-EZ-16-Homopolymer-Polypropylene-30-Calcium-Carbonate-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.135 g/cc	0.04100 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.040 %	0.040 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	52	52	ASTM D785
Hardness, Rockwell R	81	81	ASTM D785
Tensile Strength, Ultimate	25.5 MPa	3700 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Flexural Strength	35.8 MPa	5190 psi	ASTM D790
Flexural Modulus	1.90 GPa	276 ksi	ASTM D790
Izod Impact, Notched	0.300 J/cm	0.562 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.30 J/cm	9.93 ft-lb/in	ASTM D256
Gardner Impact	2.70 J	1.99 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Melting Point	182 °C	360 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	219 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	66.0 °C	151 °F	ASTM D648
Flammability, UL94	HB	HB	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China