

Adell WR-37 33% Glass Reinforced PET

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 30% Glass Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Adell-WR-37-33-Glass-Reinforced-PET.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.58 g/cc	1.58 g/cc	ASTM D792
Water Absorption	0.050 %	0.050 %	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0030 cm/cm	0.0020 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	112	112	ASTM D785
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Ultimate	160 MPa	23200 psi	ASTM D638
Flexural Strength	240 MPa	34800 psi	ASTM D790
Flexural Modulus	9.20 GPa	1330 ksi	ASTM D790
Compressive Yield Strength	233 MPa	33800 psi	ASTM D695
Izod Impact, Notched	0.961 J/cm @Thickness 3.17 mm	1.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	232 - 249 °C	450 - 480 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	247 °C	477 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	225 °C	437 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China