

## Advanced Elastomer Systems Santoprene® 8281-75 Thermoplastic Rubber (discontinued \*\*)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

### Material Notes:

Description: A colorable thermoplastic medical grade elastomer. It has USP Class VI Certificate of Compliance for biocompatibility and can be processed using injection molding, extrusion, or other melt processing techniques. Supplied as free-flowing pellets in 25 kilogram (55 pound) moisture barrier bags. Features: Non-hygroscopic product, requires little to no drying before processing Neutral, easy coloring formulation USP Class VI Certificate of Compliance Drug Master File established with FDA Product Notes: Values are for injection molded plaques, side gated. 82.6 mm x 117.5 mm x 3 mm Information provided by Advanced Elastomer Systems. Advanced Elastomer Systems is now a part of ExxonMobil. This grade was removed from the Advanced Elastomers Systems standard product line before the ExxonMobil acquisition.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Advanced-Elastomer-Systems-Santoprene-8281-75-Thermoplastic-Rubber-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Advanced-Elastomer-Systems-Santoprene-8281-75-Thermoplastic-Rubber-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	5 seconds; ASTM D2240
	80	80	5 seconds, After oven air aging 168 hours @ 150°C; ASTM D2240
Tensile Strength at Break	5.40 MPa	783 psi	After oven air again 168 hrs. @ 150°C; ASTM D412
	6.00 MPa	870 psi	Across flow; ASTM D412
Tensile Strength, Yield	4.00 MPa	580 psi	At 100% elongation, across flow; ASTM D412
Elongation at Break	292.5 %	292.5 %	After oven air aging 168 hrs. @ 150°C; ASTM D412
	450 %	450 %	Across flow; ASTM D412
Tear Strength	35.1 kN/m	200 pli	73°F; ASTM D624
Compression Set	28 %	28 %	73°F, 170 hr, Method B; ASTM D395
Tensile Set	25 %	25 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Processing Temperature	177 - 232 °C	351 - 450 °F	
Drying Temperature	82.0 °C	180 °F	Desiccant Dryer
Dry Time	3 hour	3 hour	Desiccant Dryer

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China