

Advanced Elastomer Systems VistaFlex® 911-B Thermoplastic Rubber (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Description: A black high-flow thermoplastic elastomer especially designed for injection molding applications. It replaces soft thermoplastics such as SBS, SEBS, and PVC blends. Supplied as free-flowing pellets in 25 kilogram (55 pound) moisture barrier bags.
Features: High flow Good surface appearance on molded parts Good tensile properties and high elongation at break Good tear strength
Product Notes: Values are for injection molded plaques, side gated. 82.6 mm x 117.5 mm x 3 mm
 Information provided by Advanced Elastomer Systems. Advanced Elastomer Systems is now a part of ExxonMobil. This grade was removed from the Advanced Elastomers Systems standard product line before the ExxonMobil acquisition.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Advanced-Elastomer-Systems-VistaFlex-911-B-Thermoplastic-Rubber-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D792
Melt Flow	15 g/10 min @Load 5.00 kg, Temperature 230 °C	15 g/10 min @Load 11.0 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94	94	5 seconds; ASTM D2240
Tensile Strength at Break	12.0 MPa	1740 psi	Across flow; ASTM D412
Tensile Strength, Yield	7.03 MPa	1020 psi	At 100% elongation, across flow; ASTM D412
Elongation at Break	600 %	600 %	Across flow; ASTM D412
Tensile Modulus	0.200 GPa	29.0 ksi	1 mm/min; DIN 53457
Flexural Modulus	0.210 GPa	30.5 ksi	1.7 mm/min; DIN 53457
Izod Impact, Notched	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 180A
Tear Strength	94.7 kN/m	540 pli	73°F; ASTM D624
Compression Set	57 %	57 %	73°F, 22 hr, Method B; ASTM D395
	81 %	81 %	158°F, 22 hr, Method B; ASTM D395
Tensile Set	50 %	50 %	ASTM D412

Thermal Properties	Metric	English	Comments
Vicat Softening Point	60.0 °C	140 °F	Vicat A, 1 kg; DIN 53460/ISO 306
Brittleness Temperature	-45.0 °C	-49.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 240 °C	347 - 464 °F	
Mold Temperature	20.0 - 40.0 °C	68.0 - 104 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China