

Advanced Polymer Alloys Alcryn® 2090 NC Melt Processable Rubber

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Alcryn melt-processable rubber (MPR) is a true rubber, based on a partially cross-linked, chlorinated olefin interpolymer alloy. Alcryn is designed for the manufacture of rubber parts with high productivity on thermoplastic processing equipment. Applications: Window and door weatherstripping (and other complex profile extrusions) Soft handles and grips Molded seals and gaskets Injection-molded and co-injection molded parts Blow-molded parts Tubing and hose Wire and cable jackets Coated fabrics and sheet goods Information provided by Advanced Polymer Alloys

Order this product through the following link:

http://www.lookpolymers.com/polymer_Advanced-Polymer-Alloys-Alcryn-2090-NC-Melt-Processable-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ASTM D471; ISO 2781
Viscosity	550000 cP	550000 cP	ASTM D3835
	@Shear Rate 300 1/s, Temperature 190 °C	@Shear Rate 300 1/s, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	88	88	ASTM D2240; ISO 48
Tensile Strength, Ultimate	0.255 MPa	37.0 psi	After 7 days at 257°F (125°C); ASTM D573; ISO 188
	10.8 MPa	1570 psi	ASTM D412; ISO 37
Elongation at Break	320 %	320 %	ASTM D412; ISO 37
100% Modulus	0.000490 GPa	0.0710 ksi	After 7 days at 257°F (125°C); ASTM D573; ISO 188
	0.00641 GPa	0.930 ksi	ASTM D412; ISO 37
Compression Set	27 %	27 %	After 22 Hr at 75°F (24°C); ASTM D395; ISO 815
	74 %	74 %	22 hrs.; ASTM D395; ISO 815
	@Temperature 100 °C	@Temperature 212 °F	
Tensile Set	13 %	13 %	ASTM D412

Thermal Properties	Metric	English	Comments
Clash Berg Stiffness Temperature	-5.00 °C	23.0 °F	At 10,000 psi (69 Mpa); ASTM D1043

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
Fluid Resistance - Volume Change, % (ASTM D471)		-10	After 7 Days in ASTM Oil No.1 at 212°F (100°C)
		-23	After 7 Days in IRM 903 Oil No.3 at 212°F (100°C)
		36	After 7 Days in ASTM Ref. Fuel No. B at 75°F (24°C)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China