

Advanced Polymer Alloys DuraGrip™ 6840 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

With its true rubber look and feel, DuraGrip® TPE improves the performance and appearance of virtually any consumer or light industrial product. Its one of the most versatile materials in APAs extensive line of Melt-Processable Elastomers™. FDA compliant grades with very good elastomeric properties and, when needed, a soft touch feel. Available in a wide variety of hardnesses

Advantages

- Soft Grips** – When combined with rigid thermoplastic substrates, DuraGrip adds an ergonomic, soft feel that increases customer value in household products, appliances, personal care items, hand tools, sporting goods, and more.
- Eye-Catching Color** – Makes this product more attractive to the customers with easily colorable natural, translucent, and clear grades.
- Faster Cycle Times** – DuraGrip flows easily and molds with precision, enabling you to realize maximum throughput and profitability.
- General purpose performance**
- FD-compliant applications**
- Bonding to polypropylene and polyethylene**
- Engineered thermoplastic bonding**
- Clear products**
- Bonding to nylon**

Information provided by Advanced Polymer Alloys

Order this product through the following link:

http://www.lookpolymers.com/polymer_Advanced-Polymer-Alloys-DuraGrip-6840-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.990 g/cc	0.990 g/cc	ASTM D471
Viscosity	112000 cP	112000 cP	ASTM D3835
	@Shear Rate 300 1/s, Temperature 190 °C	@Shear Rate 300 1/s, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	42	42	5 Sec; ASTM D2240
Tensile Strength at Break	5.18 MPa	752 psi	ASTM D412
Elongation at Break	452 %	452 %	ASTM D412
100% Modulus	0.00124 GPa	0.180 ksi	ASTM D412
Graves Tear Strength	15.3 kN/m	87.0 pli	Die C; ASTM D624
	@Temperature 24.0 °C	@Temperature 75.2 °F	
Compression Set	14 %	14 %	after 22 Hr At 24°C; ASTM D395
Tensile Set	7.0 %	7.0 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-67.0 °C	-88.6 °F	ASTM D746

Descriptive Properties	Value	Comments
------------------------	-------	----------

Descriptive Properties

Value

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China