

Aearo E-A-R Specialty Composites VersaDamp™ V-2325 TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

VersaDamp TPEs are olefinic dynamic vulcanizates. The VersaDamp 2000 series materials provide predictable damping performance throughout a broad range of temperatures. They can be injection molded into a wide variety of standard or custom isolators, including grommets, equipment mounts, bumpers, and gaskets. They feature high internal damping properties for low amplification at resonance to protect equipment during frequency cycling and random shocks, effective shock protection for sensitive mechanisms within minimum sway parameters, and quick return to equilibrium after vibrations or shocks. Information provided by Aearo E-A-R Specialty Composites.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aearo-E-A-R-Specialty-Composites-VersaDamp-V-2325-TPE.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	5 sec.; ASTM D2240
Tensile Strength at Break	2.62 MPa	380 psi	ASTM D412
Elongation at Break	278 %	278 %	ASTM D412
Tensile Modulus	0.00134 GPa	0.195 ksi	ASTM D412
Compressive Yield Strength	0.100 MPa	14.5 psi	Compressive Load Deflection at 5%; ASTM D575
	0.210 MPa	30.5 psi	Compressive Load Deflection at 10%; ASTM D575
	0.320 MPa	46.4 psi	Compressive Load Deflection at 15%; ASTM D575
	0.450 MPa	65.3 psi	Compressive Load Deflection at 20%; ASTM D575
	0.620 MPa	89.9 psi	Compressive Load Deflection at 25%; ASTM D575
Compressive Modulus	0.00220 GPa	0.319 ksi	at 15% Compression; ASTM D575
Resilience	40	40	% Bashore Rebound; 22°C; ASTM D2632
	53	53	% Bashore Rebound; 70°C; ASTM D2632
Tear Strength	10.2 kN/m	58.2 pli	ASTM D624
Compression Set	5.0 %	5.0 %	24 hour at 20°C; ASTM D395B
	9.9 %	9.9 %	1/2 hour at 20°C; ASTM D395B

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Maximum Service Temperature, Air Thermal Properties	100 °C Metric	212 °F English	Continuous Comments
	125 °C	257 °F	Intermittent
Brittleness Temperature	<= -40.0 °C	<= -40.0 °F	ASTM D2137
Flammability, UL94	HB	HB	Meets HBF

Descriptive Properties	Value	Comments
MVSS 302 Flammability	Passes	
Relative Peak Transmissibility	12.7 dB	G-411 Grommet; 1.2lb load @ 20°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China