

Aearo E-A-R Specialty Composites VersaDamp™ V-2725 TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

VersaDamp TPEs are olefinic dynamic vulcanizates. The VersaDamp 2000 series materials provide predictable damping performance throughout a broad range of temperatures. They can be injection molded into a wide variety of standard or custom isolators, including grommets, equipment mounts, bumpers, and gaskets. They feature high internal damping properties for low amplification at resonance to protect equipment during frequency cycling and random shocks, effective shock protection for sensitive mechanisms within minimum sway parameters, and quick return to equilibrium after vibrations or shocks. Information provided by Aearo E-A-R Specialty Composites.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aearo-E-A-R-Specialty-Composites-VersaDamp-V-2725-TPE.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	5 sec.; ASTM D2240
Tensile Strength at Break	6.73 MPa	976 psi	ASTM D412
Elongation at Break	381 %	381 %	ASTM D412
Tensile Modulus	0.00379 GPa	0.549 ksi	ASTM D412
Compressive Yield Strength	0.390 MPa	56.6 psi	Compressive Load Deflection at 5%; ASTM D575
	0.770 MPa	112 psi	Compressive Load Deflection at 10%; ASTM D575
	1.17 MPa	170 psi	Compressive Load Deflection at 15%; ASTM D575
	1.66 MPa	241 psi	Compressive Load Deflection at 20%; ASTM D575
	2.33 MPa	338 psi	Compressive Load Deflection at 25%; ASTM D575
Compressive Modulus	0.00760 GPa	1.10 ksi	at 15% Compression; ASTM D575
Resilience	35	35	% Bashore Rebound; 22°C; ASTM D2632
	50	50	% Bashore Rebound; 70°C; ASTM D2632
Tear Strength	24.9 kN/m	142 pli	ASTM D624
Compression Set	14.5 %	14.5 %	24 hour at 20°C; ASTM D395B
	20.1 %	20.1 %	1/2 hour at 20°C; ASTM D395B

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Maximum Service Temperature, Air Thermal Properties	100 °C Metric	212 °F English	Continuous Comments
	125 °C	257 °F	Intermittent
Brittleness Temperature	<= -40.0 °C	<= -40.0 °F	ASTM D2137
Flammability, UL94	HB	HB	Meets HBF

Descriptive Properties	Value	Comments
MVSS 302 Flammability	Passes	
Relative Peak Transmissibility	11.2 dB	G-411 Grommet; 1.2lb load @ 20°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China