Akro-Plastic Akroloy® PA GF 40 (2845) PA 6.6 & PA6I/6T Conditioned, 40% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

Material Notes:

One of the most characteristic properties of polyamide (PA 6.6) is the absorption of moisture. This essentially leads to increased toughness and elongation at break, to name the most important parameters. On the other side, there are important diminished design properties, such as rigidity, strength and creep modulus. It is also clear that the water molecules diffused into the polymer require a certain space, so that the dimensional stability suffers, as well. Applications that up to now have been manufactured of die-cast metals, usually involve extremely high demands on synthetic materials, running contrary to the above mentioned disadvantages. Even high levels of reinforcement in standard polyamides on the basis of PA 6 or PA 6.6 with, for example, 50 % or 60 % glass fibres, still exhibit drastic changes in mechanical characteristics. By blending of PA 6.6 with a partially aromatic CoPA (PA 6I/6T), it is possible to significantly reduce the influence of moisture on the product characteristics. While the drop in rigidity and strength of PA 6.6 GF 50 in a standard climate is still at approx. 25 %, a partially aromatic blend nevertheless exhibits a drop of less than 10 %. Furthermore, it becomes apparent that the toughness remains virtually unaffected. As a result of these findings, the swelling behaviour is improved, as well, which is favourable for dimensional stability. At the same time, this material mix also increases the glass transition temperature range. All in all, partly aromatic PA 6.6-Blends offer exactly the characteristics that are demanded by designers and users. Processing: AKROLOY® PA is based on a semi-crystalline PA 6.6 and an amorphous CoPA. This essentially determines the processing conditions. Accordingly, the melting point of AKROLOY® PA is at approx. 255 °C and is not influenced by the CoPA. With increasing temperatures, the amorphous contents provide a disproportionately low viscosity. The result is a very good reproduction of mould surfaces and a mass temperature that is up to 30 °C lower than required by comparable products. This results, aside from high quality surface finishes, frequently in reductions of cycle times, as well. Owing to production conditions, this must be verified in each individual case. Overall, AKROLOY® PA represents a step towards energy savings, in particular, when energy costs are compared to those in metal production and processing. Due to increasing cost pressure in many industrial sectors, AKROLOY® PA will become a very interesting alternative material in the area of substitutes for metal diecasting. Aside from already mentioned advantages in the service life of the mould, the omission of post processing allows an average cost reduction of up to 50 % - and more. The following list comprises imaginable and suitable areas of application, grouped by segments. Applications: Automotive Industry:Ignition key switch housingDoor handle componentsdoor lock componentsInstrument panels (centre console)Arm restsElectric motor housingsWiper componentsCarriers for wood decor stripsSeat sliding mechanisms, etc.Sanitary Installation:Single lever tapsWater filter housingsHousing for bath tapChrome-plated shower heads, levels, etc. Construction:Window locksDoor lock componentsExpanding nails for insulating plugsCorner connectors for lighting systemsShelving support elements, etc.Household:HandlesCoffee maker componentsJuice extractor componentsKnives and handlesBottle openersNutcrackers, etc. Electronic Industry:Mobile phone housingsPlastic tongsHousings for measuring unitsCarrier plates, etc. Machine Building:Plastic screwsCalipersScrew clamps, etc.Information from Akro-Plastic

Order this product through the following link: http://www.lookpolymers.com/polymer_Akro-Plastic-Akroloy-PA-GF-40-2845-PA-66-PA6I6T-Conditioned-40-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in³	ISO 183
Filler Content	40 %	40 %	ISO 1172

SONGHAN Plastic Technology Co., Ltd.

www.lookpolymers.com email:sales@lookpolymers.com

Physical Properties Water Absorption	Metric	English	Comments 50% r.h.; ISO 62
•	@Temperature 23.0 °C	@Temperature 73.4 °F	
Water Absorption at Saturation	4.0 - 4.5 %	4.0 - 4.5 %	ISO 62
Linear Mold Shrinkage, Flow	<= 0.0010 cm/cm	<= 0.0010 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	200 MPa	29000 psi	5 [mm/min]; ISO 527-1/2
	100 MPa	14500 psi	5 [mm/min], 50% Loss of Tensile Strength; ICE 216
	@Temperature 140 - 150 °C, Time 1.80e+7 sec	@Temperature 284 - 302 °F, Time 5000 hour	
	100 MPa	14500 psi	
	@Temperature 140 - 150 °C, Time 7.20e+7 sec	@Temperature 284 - 302 °F, Time 20000 hour	5 [mm/min], 50% Loss of Tensile Strength; ICE 216
Elongation at Break	3.0 %	3.0 %	5 [mm/min]; ISO 527-1/2
Tensile Modulus	12.0 GPa	1740 ksi	1[mm/min]; ISO 527-1/2
Charpy Impact Unnotched	9.00 J/cm ²	42.8 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.40 J/cm ²	6.66 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	ISO 11357-1, DSC,10 [K/min]

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China