

Akro-Plastic Akromid® T1 GF 40 9 (3499) PPA Dry, 40% Glass Filled

Category : Polymer , Thermoplastic , Polyphthalamide (PPA) , Polyphthalamide (PPA), 40% Glass Fiber Reinforced

Material Notes:

The new AKROMID® T is characterized primarily by high heat resistance and the lowest moisture absorption of the three PA grades, making it particularly well-suited in the automotive sector for high-temperature applications in the engine compartment and in machine building for components subjected to high mechanical loads. It easily maintains its high initial stability even at temperatures of up to 140 °C and still exhibits phenomenal creep behaviour. This extremely high dimensional stability is further enhanced by the product's low moisture absorption. Another key advantage over PA 6 or PA 6.6 is the significantly improved chemical resistance and high resistance to hydrolytic degradation. These properties – along with the aforementioned advantages in terms of mechanical loading – make the material an ideal answer for difficult applications in industrial pumps and fluid filters. Its low water absorption over extended periods is yet another advantage. By modifying the base grades, we have also made the material suitable for applications requiring a high quality surface finish.

Applications:

Automotive Sector: Cooling system (thermostat housing, connectors, etc.) Parts in the oil circuit (tensioner bases, etc.) Parts in the brake system (valve bodies, etc.) Clutch components (central clutch release bearing, etc.) Air ducting parts (side pieces for charge-air coolers, control shafts, etc.) Parts subjected to high loads in the interior (centre armrest, etc.)

Electrical Engineering: Mobile telephone parts (chip carrier, etc.) Coil formers Motor parts (brush holders, etc.) Plugs and connectors Bulb and LED sockets

Industry and Household: Heating systems (fan housings, etc.) Components for coffee machines (grades compliant with KTW- German recommendation for polymers in drinking-water systems) Water counters and water filters (KTW-compliant, hot water) Pump systems (misc. functional parts)

Information from Akro-Plastic

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akro-Plastic-Akromid-T1-GF-40-9-3499-PPA-Dry-40-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.52 g/cc @Temperature 23.0 °C	0.0549 lb/in ³ @Temperature 73.4 °F	ISO 1183
Filler Content	40 %	40 %	ISO 1172
Water Absorption	1.1 % @Temperature 70.0 °C	1.1 % @Temperature 158 °F	62% r.h., Humidity; ISO 62
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	310 MPa	45000 psi	H 961/30; ISO 2039-1
Tensile Strength at Break	250 MPa	36300 psi	5 [mm/min]; ISO 527-1/2
	125 MPa @Temperature 150 - 160 °C,	18100 psi @Temperature 302 - 320 °F,	5 [mm/min], 50% Loss of Tensile Strength; ICE 216

Mechanical Properties	Time 1.80e+7 sec Metric	Time 5000 hour English	Comments
	125 MPa	18100 psi	
	@Temperature 130 - 140 °C, Time 7.20e+7 sec	@Temperature 266 - 284 °F, Time 20000 hour	5 [mm/min], 50% Loss of Tensile Strength; ICE 216
Elongation at Break	2.4 %	2.4 %	5 [mm/min]; ISO 527-1/2
	2.9 %	2.9 %	2 [mm/min], Flexural; ISO 178
Tensile Modulus	15.0 GPa	2180 ksi	1[mm/min]; ISO 527-1/2
Flexural Strength	360 MPa	52200 psi	2 [mm/min]; ISO 178
Flexural Modulus	14.5 GPa	2100 ksi	2 [mm/min]; ISO 178
Charpy Impact Unnotched	5.50 J/cm ²	26.2 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	7.00 J/cm ²	33.3 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.10 J/cm ²	5.24 ft-lb/in ²	ISO 179-1/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	1.10 J/cm ²	5.24 ft-lb/in ²	ISO 179-1/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	308 °C	586 °F	ISO 11357-1, DSC,10 [K/min]
Deflection Temperature at 1.8 MPa (264 psi)	275 °C	527 °F	HDT/A; ISO 75-1/2
Deflection Temperature at 8.0 MPa	195 °C	383 °F	HDT/C; ISO 75-2
Flammability, UL94	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	Test Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Feed Temperature	80.0 - 95.0 °C	176 - 203 °F	
Nozzle Temperature	320 - 330 °C	608 - 626 °F	

Processing Properties	Metric	English	Comments
Zone 2	315 - 325 °C	599 - 617 °F	
Zone 3	320 - 335 °C	608 - 635 °F	
Zone 4	320 - 335 °C	608 - 635 °F	
Melt Temperature	325 - 340 °C	617 - 644 °F	
Mold Temperature	100 - 130 °C	212 - 266 °F	
Drying Temperature	90.0 °C	194 °F	
Dry Time	2 - 16.0 hour	2 - 16.0 hour	
Hold Pressure	30.0 - 80.0 MPa	4350 - 11600 psi	
Back Pressure	0.200 - 0.650 MPa	29.0 - 94.3 psi	

Descriptive Properties	Value	Comments
Acetic acid	Fail	100% Conc
Acetone	Pass	100% Conc
Cresol	Fail	100% Conc
Diesel fuel (DIN 51601)	Pass	100% Conc
Drying, Moisture (%)	<0.1	
Engine oil	Pass	100% Conc
Ethanol	Pass	96% Conc
Ethylene glycol/water	Pass	120°C, 50% Conc
Formic acid	Fail	100% Conc
Hydraulic oil	Pass	100% Conc
Injection Speed	average to high	
Isopropanol	Pass	100% Conc
Kerosene	Pass	100% Conc
Methanol	Pass	100% Conc
Petrol	Pass	100% Conc
Phenol	Fail	100% Conc

Rate acc. FMVSS 302 (Descriptive Properties)	Passed Value	Comments
Rate acc. FMVSS 302,(FMVSS 302, >1 [mm] Thickness	
Silicone oil	Pass	
Sulphuric acid	Fail	96% Conc
Toluene	Pass	100% Conc
Urea, aqueous	Pass	20% Conc
Water	Pass	100% Conc
Xylene	Pass	100% Conc
Zinc chloride, aqueous	Pass	50% Conc

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China