

## Akzo Nobel Trigonox® 121 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

### Material Notes:

Initiator for the (co)polymerization of ethylene, styrene, acrylates and methacrylates. Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Akzo-Nobel-Trigonox-121-Polymerization-Initiator.php](http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-121-Polymerization-Initiator.php)

Physical Properties	Metric	English	Comments
Density	0.914 g/cc @Temperature 0.000 °C	0.0330 lb/in <sup>3</sup> @Temperature 32.0 °F	
Viscosity	9.0 cP @Temperature 0.000 °C	9.0 cP @Temperature 32.0 °F	
Molecular Weight	230.3 g/mol	230.3 g/mol	
One Hour Half Life Temperature	91.0 °C	196 °F	
Storage Temperature	-10.0 - 5.00 °C	14.0 - 41.0 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China