

## Akzo Nobel Trigonox® 301 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

### Material Notes:

Initiator for the production of controlled rheology polypropylene (CR-PP). Chemical description: 3,6,9-Triethyl-3,6,9-trimethyl-1,4,7-triperoxonane, 41% solution in isoparaffinic hydrocarbons CAS Number: 24748-23-0 Acronym: Tx 301 Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Akzo-Nobel-Trigonox-301-Polymerization-Initiator.php](http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-301-Polymerization-Initiator.php)

Physical Properties	Metric	English	Comments
Density	0.875 g/cc @Temperature 20.0 °C	0.0316 lb/in <sup>3</sup> @Temperature 68.0 °F	
Viscosity	5.0 cP @Temperature 20.0 °C	5.0 cP @Temperature 68.0 °F	
Molecular Weight	264.3 g/mol	264.3 g/mol	
One Hour Half Life Temperature	146 °C	295 °F	
Storage Temperature	10.0 - 40.0 °C	50.0 - 104 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China