

Akzo Nobel Trigonox® B Polymerization Initiator

Category: Other Engineering Material, Catalyst/Initiator, Polymer

Material Notes:

Initiator for the (co)polymerization of ethylene, styrene, acrylates and methacrylates. Trigonox B is a monofunctional peroxide which is used for the crosslinking of polyolefins as well as natural rubber and synthetic rubbers. Chemical Description: Di-tert-butyl peroxideCAS Number: 110-05-4Acronym: DTBP; Tx BInformation provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-B-Polymerization-Initiator.php

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	141 °C	286 °F	
Storage Temperature	-30.0 - 40.0 °C	-22.0 - 104 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China