

Akzo Nobel Trigonox® BPIC-C75 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

Material Notes:

Initiator for the (co)polymerization of ethylene, styrene, acrylonitrile, acrylates and methacrylates. Trigonox BPIC-C75 may also be used as an initiator for curing unsaturated polyester and vinylester resins at elevated temperatures. Chemical Description: tert-Butylperoxy isopropyl carbonate, 75% solution in odorless mineral spirits CAS Number: 2372-21-6 Acronym: BPIC; Tx BPIC Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-BPIC-C75-Polymerization-Initiator.php

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	117 °C	243 °F	
Storage Temperature	-20.0 - 25.0 °C	-4.00 - 77.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China