

## Akzo Nobel Trigonox® D-E50 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

### Material Notes:

Initiator for the (co)polymerization of ethylene, styrene, acrylonitrile, acrylates and methacrylates. Chemical Description: 2,2-Di(tert-butylperoxy)butane, 50% solution in mineral oil CAS Number: 2167-23-9 Acronym: Tx DI Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Akzo-Nobel-Trigonox-D-E50-Polymerization-Initiator.php](http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-D-E50-Polymerization-Initiator.php)

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	116 °C	241 °F	
Storage Temperature	<= 30.0 °C	<= 86.0 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China