

Akzo Nobel Trigonox® EHP-C65 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

Material Notes:

Initiator for the (co)polymerization of ethylene, vinylchloride, vinylidenechloride, acrylates and methacrylates. Chemical Description: Di(2-ethylhexyl) peroxydicarbonate, 65% solution in odorless mineral spirits CAS Number: 16111-62-9 Acronym: EHP; OPP; Tx EHP Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-EHP-C65-Polymerization-Initiator.php

| Physical Properties | Metric | English | Comments |
|--------------------------------|------------------|-----------------|----------|
| One Hour Half Life Temperature | 64.0 °C | 147 °F | |
| Storage Temperature | -25.0 - -15.0 °C | -13.0 - 5.00 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China