

Akzo Nobel Trigonox® EHP-C75 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

Material Notes:

Initiator for the (co)polymerization of ethylene, vinylchloride, vinylidenechloride, acrylates and methacrylates. Trigonox EHP-C75 is a low temperature initiator for curing unsaturated polyester and vinylester resins at slightly elevated temperatures. Chemical Description: Di(2-ethylhexyl) peroxydicarbonate, 75% solution in odorless mineral spiritsCAS Number: 16111-62-9Acronym: EHP; OPP; Tx EHPInformation provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-EHP-C75-Polymerization-Initiator.php

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	64.0 °C	147 °F	
Storage Temperature	-25.0 - -15.0 °C	-13.0 - 5.00 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China