

## Akzo Nobel Trigonox® EHP-W40 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

### Material Notes:

Initiator for the (co)polymerization of vinylchloride and vinylidenechloride. Chemical Description: Di(2-ethylhexyl) peroxydicarbonate, 40% emulsion in water and methanol CAS Number: 16111-62-9 Acronym: EHP; OPP; Tx EHP Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Akzo-Nobel-Trigonox-EHP-W40-Polymerization-Initiator.php](http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-EHP-W40-Polymerization-Initiator.php)

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	64.0 °C	147 °F	
Storage Temperature	-20.0 - -15.0 °C	-4.00 - 5.00 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China