

Akzo Nobel Trigonox® F-C30 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

Material Notes:

Initiator for the (co)polymerization of ethylene, styrene and other vinyl monomers. Chemical Description: tert-Butyl peroxyacetate, 30% solution in odorless mineral spirits CAS Number: 107-71-1 Acronym: TBPA; Tx F Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-F-C30-Polymerization-Initiator.php

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	119 °C	246 °F	
Storage Temperature	<= 10.0 °C	<= 50.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China