

Akzo Nobel Trigonox® K-80 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

Material Notes:

Initiator for the (co)polymerization of styrene, butadiene, acrylonitrile, vinylacetate, acrylates and methacrylates. Trigonox K-80 may also be used for the room temperature cure of promoted unsaturated polyester and vinylester resins, and elevated temperature cure of non-promoted resins. Chemical Description: Cumyl hydroperoxide, 80% solution in aromatic solvent mixture CAS Number: 13122-18-4 Acronym: CHP; Tx K80 Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-K-80-Polymerization-Initiator.php

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	166 °C	331 °F	
Storage Temperature	-30.0 - 40.0 °C	-22.0 - 104 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China