

Albis Plastics ASA 02A 811 Unreinforced (discontinued **)

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

Acrylonitrile/Styrene/Acrylate Characteristics: Excellent UV, Good Rigidity, Good Dimensional Stability Applications: Sunglasses, Boat Shells, Roofs for Campers & RVs Processing: Injection Molding (Melt Temperature: 465-535°F, Mold Temperature: 105-175°F) Data supplied by Albis Plastics Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Albis-Plastics-ASA-02A-811-Unreinforced-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Melt Flow	10 g/10 min	10 g/10 min	220C/10,000 g; ASTM D1238

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	2.14 J/cm	4.01 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	84.0 °C	183 °F	ASTM D648
Vicat Softening Point	98.0 °C	208 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	241 - 279 °C	466 - 534 °F	Injection
Mold Temperature	41.0 - 79.0 °C	106 - 174 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China