

## Albis Plastics Cellulose Acetate Butyrate B900 (Base Grade), 20% Plasticizer (discontinued \*\*)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate Butyrate, Molded

### Material Notes:

Amorphous Cellulose Acetate Butyrate (CAB) Characteristics: Dimensional Stability, Weatherability and Low Temp Impact

Strength Applications: Pens, Ski Goggles, Auto Trim, Skylights, Tool Handles and Toys Processing: Injection Molding (Melt Temperature: 395°F, Mold Temperature: 100°F) Data supplied by Albis Plastics Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Albis-Plastics-Cellulose-Acetate-Butyrate-B900-Base-Grade-20-Plasticizer-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Albis-Plastics-Cellulose-Acetate-Butyrate-B900-Base-Grade-20-Plasticizer-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.2 %	1.2 %	(24 hr); ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	26.9 MPa	3900 psi	ASTM D638
Tensile Strength, Yield	16.5 MPa	2390 psi	ASTM D638
Flexural Yield Strength	25.5 MPa	3700 psi	ASTM D790
Flexural Modulus	0.970 GPa	141 ksi	ASTM D790
Izod Impact, Notched	5.23 J/cm	9.80 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	58.0 °C	136 °F	ASTM D648
Vicat Softening Point	92.0 °C	198 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	202 °C	396 °F	Injection
Mold Temperature	38.0 °C	100 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**