

Albis Plastics Cellulose Acetate Butyrate B9024 (UVI, Odor Mask Added), 13% Plasticizer (discontinued **)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate Butyrate, Molded

Material Notes:

Amorphous Cellulose Acetate Butyrate (CAB) Characteristics: Dimensional Stability, Weatherability and Low Temp Impact

Strength Applications: Pens, Ski Goggles, Auto Trim, Skylights, Tool Handles and Toys Processing: Injection Molding (Melt Temperature: 430°F, Mold Temperature: 125°F) Data supplied by Albis Plastics Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Albis-Plastics-Cellulose-Acetate-Butyrate-B9024-UVI-Odor-Mask-Added-13-Plasticizer-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|-----------------------|-----------------------|---------------------------|--------------------|
| Density | 1.18 g/cc | 0.0426 lb/in ³ | ASTM D792 |
| Water Absorption | 1.4 % | 1.4 % | (24 hr); ASTM D570 |
| Linear Mold Shrinkage | 0.0020 - 0.0060 cm/cm | 0.0020 - 0.0060 in/in | ASTM D955 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-----------|---------------|-----------|
| Tensile Strength at Break | 34.5 MPa | 5000 psi | ASTM D638 |
| Tensile Strength, Yield | 24.8 MPa | 3600 psi | ASTM D638 |
| Flexural Yield Strength | 32.8 MPa | 4760 psi | ASTM D790 |
| Flexural Modulus | 1.10 GPa | 160 ksi | ASTM D790 |
| Izod Impact, Notched | 3.74 J/cm | 7.01 ft-lb/in | ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|---|---------|---------|------------|
| Deflection Temperature at 1.8 MPa (264 psi) | 69.0 °C | 156 °F | ASTM D648 |
| Vicat Softening Point | 100 °C | 212 °F | ASTM D1525 |

| Processing Properties | Metric | English | Comments |
|-----------------------|---------|---------|-----------|
| Melt Temperature | 221 °C | 430 °F | Injection |
| Mold Temperature | 52.0 °C | 126 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China