

Albis Plastics Cellulose Acetate Butyrate B9324 (UVI, Odor Mask Added), 4% Plasticizer (discontinued **)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate Butyrate, Molded

Material Notes:

Amorphous Cellulose Acetate Butyrate (CAB) Characteristics: Dimensional Stability, Weatherability and Low Temp Impact

Strength Applications: Pens, Ski Goggles, Auto Trim, Skylights, Tool Handles and Toys Processing: Extrusion (Melt Temperature: 470°F) Data supplied by Albis Plastics Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Albis-Plastics-Cellulose-Acetate-Butyrate-B9324-UVI-Odor-Mask-Added-4-Plasticizer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ASTM D792
Water Absorption	1.8 %	1.8 %	(24 hr); ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	51.0 MPa	7400 psi	ASTM D638
Tensile Strength, Yield	42.7 MPa	6190 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Yield Strength	60.0 MPa	8700 psi	ASTM D790
Flexural Modulus	1.79 GPa	260 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	84.0 °C	183 °F	ASTM D648
Vicat Softening Point	115 °C	239 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	243 °C	469 °F	Injection

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China