

Albis Plastics Tedur® L 9561 PPS, 60% Glass Fiber/Mineral (discontinued **)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), Mineral/Glass-Fiber Filled

Material Notes:

High Gloss, Highest Surface Finish, Metallization w/o Base Coating. Incandescent wire resistance (2 mm) is 960°C per VDE 0471

T1.2.Applications: Various High Temperature Reflectors Processing: Injection Molding (Melt Temperature: 610-645°F, Mold Temperature: 285°F) Tedur® is manufactured by Albis Plastics Corporation under license of the registered trademark owner (Bayer.) Data supplied by Albis Plastics Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Albis-Plastics-Tedur-L-9561-PPS-60-Glass-FiberMineral-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.94 g/cc	0.0701 lb/in ³	DIN 53 47

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	DIN 53 455
Elongation at Break	1.2 %	1.2 %	DIN 53 455
Modulus of Elasticity	14.0 GPa	2030 ksi	DIN 53 457
Flexural Yield Strength	130 MPa	18900 psi	DIN 53 452
Flexural Modulus	14.0 GPa	2030 ksi	DIN 53 457
Izod Impact, Notched	1.17 J/cm	2.19 ft-lb/in	Approximation; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	150 V	150 V	IEC 112

Processing Properties	Metric	English	Comments
Melt Temperature	321 - 341 °C	610 - 646 °F	Injection
Mold Temperature	141 °C	286 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China