

## Aleris Alustar Aluminum Alloy, O/H111

Category : Metal , Nonferrous Metal , Aluminum Alloy , 5000 Series Aluminum Alloy

### Material Notes:

At least 20% stronger than AA 5083 before and after welding. Bendability and weldability similar to AA 5083. High corrosion resistance. Provides options for ship design and building. Composition differs from standard 5083 and 5383 mainly in terms of higher Mg-content, higher Mn-content, higher Zn-content, and defined Zr-content. The increased Mg-content in the Alustar alloy increases the strength after welding. Together with an increased Mn-content, a higher Mg-content enhances the ductility. To compensate for the deterioration in corrosion resistance caused by the higher Mg-content, an optimal amount of Zn is required. By precipitating Mg-Zn-containing phases in the Al matrix, potential differences between the grain boundaries and grain interiors are eliminated. Zr additions to Alustar alloy cause the formation of a finer grained heat affected zone which leads to a stronger bond in the fusion zone. The effect of Zr is the same in welding wires. Therefore, in addition to the standard filler alloys such as AA5183, Zr-containing filler wires (such as AA 5087) can also be used to weld Alustar alloy plates.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aleris-Alustar-Aluminum-Alloy-OH111.php](http://www.lookpolymers.com/polymer_Aleris-Alustar-Aluminum-Alloy-OH111.php)

Physical Properties	Metric	English	Comments
Density	2.66 g/cc	0.0961 lb/in <sup>3</sup>	Aluminum 5083

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	>= 330 MPa	>= 47900 psi	
Tensile Strength, Yield	>= 160 MPa	>= 23200 psi	
Elongation at Break	24 %	24 %	
Shear Strength	198 MPa	28700 psi	Calculated

Component Elements Properties	Metric	English	Comments
Aluminum, Al	93 %	93 %	
Chromium, Cr	<= 0.30 %	<= 0.30 %	
Copper, Cu	<= 0.40 %	<= 0.40 %	
Iron, Fe	<= 0.50 %	<= 0.50 %	
Magnesium, Mg	5.0 - 6.0 %	5.0 - 6.0 %	
Manganese, Mn	0.60 - 1.2 %	0.60 - 1.2 %	
Silicon, Si	<= 0.50 %	<= 0.50 %	
Titanium, Ti	<= 0.20 %	<= 0.20 %	

<small>Zinc, Zn</small> Component Elements Properties	<small>0.40 - 1.5 %</small> Metric	<small>0.40 - 1.5 %</small> English	Comments
Zirconium, Zr	0.050 - 0.25 %	0.050 - 0.25 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China