

Aleris Weldural Aluminum Alloy, 600 mm Thickness

Category : Metal , Nonferrous Metal , Aluminum Alloy , 2000 Series Aluminum Alloy

Material Notes:

Sample treatment not specified for property data. Applications include precise mechanical parts with high dimensional stability, machine components, molds, and refrigeration engineering. Good weldability and machinability. Fair corrosion resistance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aleris-Weldural-Aluminum-Alloy-600-mm-Thickness.php

Physical Properties	Metric	English	Comments
Density	2.84 g/cc	0.103 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	130	130	
Hardness, Knoop	163	163	Estimated from Brinell
Hardness, Rockwell A	49.4	49.4	Estimated from Brinell
Hardness, Rockwell B	79	79	Estimated from Brinell
Hardness, Vickers	149	149	Estimated from Brinell
Tensile Strength, Ultimate	395 MPa	57300 psi	Typical
Tensile Strength, Yield	315 MPa @Strain 0.200 %	45700 psi @Strain 0.200 %	Typical
Elongation at Break	3.5 %	3.5 %	Typical
Modulus of Elasticity	73.8 GPa	10700 ksi	
Machinability	70 %	70 %	

Thermal Properties	Metric	English	Comments
CTE, linear	22.5 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature 20.0 - 100 $^\circ\text{C}$	12.5 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature 68.0 - 212 $^\circ\text{F}$	
Thermal Conductivity	130 W/m-K	902 BTU-in/hr-ft ² - $^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	93 %	93 %	
Copper, Cu	5.8 - 6.8 %	5.8 - 6.8 %	

Component Elements Properties	Metric %	English %	Comments
Magnesium, Mg	<= 0.10 %	<= 0.10 %	
Manganese, Mn	0.20 - 0.40 %	0.20 - 0.40 %	
Other, total	<= 0.15 %	<= 0.15 %	
Silicon, Si	<= 0.30 %	<= 0.30 %	
Titanium, Ti	0.020 - 0.10 %	0.020 - 0.10 %	
Zinc, Zn	<= 0.10 %	<= 0.10 %	
Zirconium, Zr	0.10 - 0.25 %	0.10 - 0.25 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000590 ohm-cm	0.00000590 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China