

## Alliance A-5DG Alnico Magnetic Material

Category : Metal , Electronic/Magnetic Alloy , Nonferrous Metal , Cobalt Alloy , Nickel Alloy

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Alliance-A-5DG-Alnico-Magnetic-Material.php](http://www.lookpolymers.com/polymer_Alliance-A-5DG-Alnico-Magnetic-Material.php)

Physical Properties	Metric	English	Comments
Density	7.30 g/cc	0.264 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	450 - 700	450 - 700	

Thermal Properties	Metric	English	Comments
CTE, linear	11.0 - 13.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	6.11 - 7.22 $\mu\text{in}/\text{in}\cdot\text{°F}$	Parallel DOM
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Maximum Service Temperature, Air	525 °C	977 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000470 - 0.0000530 ohm-cm	0.0000470 - 0.0000530 ohm-cm	
Magnetic Coercive Force, Hc	680 Oe	680 Oe	
	700 Oe	700 Oe	Intrinsic
Magnetic Remanence, Br	13000 Gauss	13000 Gauss	
Magnetic Maximum Energy Product, BH	6.5 MGOe	6.5 MGOe	
Curie Temperature	860 °C	1580 °F	

Descriptive Properties	Value	Comments
Reversible Temp Coef., Bd	-0.02 %/°C	
Reversible Temp Coef., Hd	+0.02 %/°C	
Temperature Coefficient, Br	-0.025 %/°C	(20-100°C)
Temperature Coefficient, Hci	+0.01 %/°C	(20-100°C)

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China