

## Alliance BCN-13 Bonded (Composite) Magnetic Material

Category : Ceramic , Metal , Electronic/Magnetic Alloy

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Alliance-BCN-13-Bonded-Composite-Magnetic-Material.php](http://www.lookpolymers.com/polymer_Alliance-BCN-13-Bonded-Composite-Magnetic-Material.php)

Physical Properties	Metric	English	Comments
Density	5.60 - 6.00 g/cc	0.202 - 0.217 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	37.0 MPa	5370 psi	
Modulus of Elasticity	0.700 - 1.00 GPa	102 - 145 ksi	
Compressive Strength	80.0 - 120 MPa	11600 - 17400 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	10.0 - 30.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 20.0 °C	5.56 - 16.7 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 68.0 °F	Parallel DOM
Specific Heat Capacity	0.400 J/g-°C	0.0956 BTU/lb-°F	
Thermal Conductivity	2.00 W/m-K	13.9 BTU-in/hr-ft <sup>2</sup> -°F	
Maximum Service Temperature, Air	140 °C	284 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00100 - 0.00300 ohm-cm	0.00100 - 0.00300 ohm-cm	
Magnetic Coercive Force, Hc	5250 Oe	5250 Oe	
	16500 Oe	16500 Oe	Intrinsic
Magnetic Remanence, Br	6100 Gauss	6100 Gauss	
Magnetic Maximum Energy Product, BH	8.5 MGOe	8.5 MGOe	
Curie Temperature	300 - 470 °C	572 - 878 °F	

Descriptive Properties	Value	Comments
Reversible Temp Coef., Bd	-0.07 %/°C	

Reversible Temp Coef., Hd Descriptive Properties	-0.40 %/°C Value	Comments
Temperature Coefficient, Br	-0.11 %/°C	(20-100°C)
Temperature Coefficient, Hci	-0.39 %/°C	(20-100°C)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China