

Alliance BIS-52 Bonded (Composite) Magnetic Material

Category : Ceramic , Metal , Electronic/Magnetic Alloy

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alliance-BIS-52-Bonded-Composite-Magnetic-Material.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Magnetic Coercive Force, Hc	4770 Oe	4770 Oe	
	9420 Oe	9420 Oe	Intrinsic
Magnetic Remanence, Br	5100 Gauss	5100 Gauss	
Magnetic Maximum Energy Product, BH	6.5 MGOe	6.5 MGOe	

Descriptive Properties	Value	Comments
Reversible Temp Coef., Bd	-0.030 %/°C	
Reversible Temp Coef., Hd	-0.30 %/°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China