

## Alliance Polymers Viprene™ G40D-32U-NAT Thermoplastic Vulcanizate Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

### Material Notes:

Viprene™ G40D-32U-NAT is a UV and Heat Stabilized TVP (Thermoplastic Vulcanizate Elastomer). This material can be easily processed by extrusion or injection molding. It exhibits easy flowing characteristics. Availability: North America Additive: Heat Stabilizer and UV Stabilizer Features: Good Flow, Good UV Resistance and Heat Stabilized Appearance: Natural Color Forms: Pellets Processing Method: Extrusion and Injection Molding Information provided by Alliance Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Alliance-Polymers-Viprene-G40D-32U-NAT-Thermoplastic-Vulcanizate-Elastomer.php](http://www.lookpolymers.com/polymer_Alliance-Polymers-Viprene-G40D-32U-NAT-Thermoplastic-Vulcanizate-Elastomer.php)

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in <sup>3</sup>	ISO 2781

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	92	92	ISO 868
Hardness, Shore D	40	40	ISO 868
Tensile Strength at Break	14.1 MPa	2050 psi	ISO 37
Tensile Stress	8.41 MPa @Strain 100 %	1220 psi @Strain 100 %	ISO 37
	10.2 MPa @Strain 300 %	1480 psi @Strain 300 %	ISO 37
Elongation at Break	500 %	500 %	ISO 37
Tear Strength	78.9 kN/m	450 pli	ISO 34-1
Compression Set	53 % @Temperature 70.0 °C, Time 79200 sec	53 % @Temperature 158 °F, Time 22.0 hour	ASTM D3995B

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746
Flammability, UL94	HB @Thickness 1.00 mm	HB @Thickness 0.0394 in	
	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Thermal Properties	Metric	English	Comments
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Processing Temperature	210 °C	410 °F	Gate Temperature; Extrusion
	210 - 240 °C	410 - 464 °F	Injection
Rear Barrel Temperature	190 °C	374 °F	Injection
Middle Barrel Temperature	195 °C	383 °F	Injection
Front Barrel Temperature	200 °C	392 °F	Injection
Nozzle Temperature	200 - 230 °C	392 - 446 °F	Injection
Zone 1	190 °C	374 °F	Extrusion
Zone 2	200 °C	392 °F	Extrusion
Zone 3	205 °C	401 °F	Extrusion
Die Temperature	215 °C @Pressure 5.00 - 20.0 MPa	419 °F @Pressure 725 - 2900 psi	Extrusion
Mold Temperature	10.0 - 50.0 °C	50.0 - 122 °F	Injection
Injection Velocity	>= 50.0 mm/sec	>= 1.97 in/sec	Injection
Drying Temperature	80.0 °C	176 °F	Injection
	80.0 °C	176 °F	Extrusion
Dry Time	3.00 hour	3.00 hour	Injection
	3.00 hour	3.00 hour	Extrusion
Back Pressure	0.300 - 0.703 MPa	43.5 - 102 psi	Injection
Clamp Pressure	40.0 - 70.3 MPa	5800 - 10200 psi	Injection
Screw Speed	100 - 200 rpm	100 - 200 rpm	Injection

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China