

Alliance Polymers Viprene™ G45A-32U-BLK Thermoplastic Vulcanizate Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

Viprene™ G45A-32U-BLK is a UV and Heat Stabilized TVP (Thermoplastic Vulcanizate Elastomer). This material can be easily processed by extrusion or injection molding. It exhibits easy flowing characteristics. Availability: North America Additive: Heat Stabilizer and UV Stabilizer Features: Good Flow, Good UV Resistance and Heat Stabilized Appearance: Black Forms: Pellets Processing Method: Extrusion and Injection Molding Information provided by Alliance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alliance-Polymers-Viprene-G45A-32U-BLK-Thermoplastic-Vulcanizate-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in ³	ISO 2781

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45	45	ISO 868
Tensile Strength at Break	4.90 MPa	711 psi	ISO 37
Tensile Stress	1.30 MPa	189 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
	2.50 MPa	363 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	550 %	550 %	ISO 37
Tear Strength	26.3 kN/m	150 pli	ISO 34-1
Compression Set	35 %	35 %	ASTM D3995B
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746
Flammability, UL94	HB	HB	
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	

Thermal Properties

Metric
@ Thickness 3.00 mm

English
@ Thickness 0.118 in

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China