

## Alliance Polymers Viprene™ P50A-22U-NAT Thermoplastic Vulcanizate Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

### Material Notes:

Viprene™ P50A-22U-NAT is a UV and Heat Stabilized TVP (Thermoplastic Vulcanizate Elastomer). This material can be easily processed by extrusion or injection molding. It exhibits easy flowing characteristics. Availability: North America Additive: Heat Stabilizer and UV Stabilizer Features: Good Flow, Good UV Resistance and Heat Stabilized Appearance: Natural Color Forms: Pellets Processing Method: Extrusion and Injection Molding Information provided by Alliance Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Alliance-Polymers-Viprene-P50A-22U-NAT-Thermoplastic-Vulcanizate-Elastomer.php](http://www.lookpolymers.com/polymer_Alliance-Polymers-Viprene-P50A-22U-NAT-Thermoplastic-Vulcanizate-Elastomer.php)

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in <sup>3</sup>	ISO 2781

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	ISO 868
Tensile Strength at Break	5.90 MPa	856 psi	ISO 37
Tensile Stress	1.80 MPa	261 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
	3.10 MPa	450 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	550 %	550 %	ISO 37
Tear Strength	31.6 kN/m	180 pli	ISO 34-1
Compression Set	19 %	19 %	ASTM D3995B
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746
Flammability, UL94	HB	HB	
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	

Thermal Properties

Metric  
@ Thickness 3.00 mm

English  
@ Thickness 0.118 in

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China